ORIGINAL

Application Based on

Docket **83664AEK**
Inventors: Xiang-Dong Mi and Tomohiro Ishikawa
Customer No. 01333

VERTICALLY ALIGNED LIQUID CRYSTAL IMAGING COMPONENT WITH COMPENSATION LAYER

Commissioner for Patents,
ATTN: BOX PATENT APPLICATION
Washington, D. C. 20231

Express Mail Label No.: _____ EL809162515US _____

Date: _Qovember 30, 2001_

VERTICALLY ALIGNED LIQUID CRYSTAL IMAGING COMPONENT WITH COMPENSATION LAYER

FIELD OF THE INVENTION

5   This invention relates to an imaging component comprising a
vertically aligned liquid crystal cell, a polarizer, and a compensation film
containing a positive birefringent material oriented with its optic axis tilted in a
plane perpendicular to the liquid crystal cell face.

10   **BACKGROUND OF THE INVENTION**

          Current rapid expansion in the liquid crystal display applications in
various areas of information display is largely due to the improvement of the
display quality. One of the major factors measuring the quality of such displays is
the viewing angle characteristic (VAC), which describes the change in a contrast

15   ratio from different viewing angles. It is desirable to be able to see the same
image from a wide variation in viewing angles and this ability has been a
shortcoming with liquid crystal display devices.

          A vertically–aligned liquid crystal display offers an extremely high
contrast ratio for normal incident light. FIG. 1 shows the schematics of display

20   configurations. In the figure, x, y and z form orthogonal coordinates **10** and z is
the direction normal to the cell surface. θ and ϕ are polar angle and azimuth
angle, respectively. A voltage source **16** is attached to the liquid crystal cell **14**.
Two polarizers **12, 18** on both sides of the liquid crystal cell **14** forms an angle of
45° with respect to the x or y direction and their transmission axes are orthogonal

25   to each other. By orthogonal, it is meant that they are 90° apart, ± 10°. In its
OFF state, the birefingent molecule's optic axis **22**, the direction in which light
does not undergo birefringence, is almost perpendicular to the substrate **20**, FIG.
2A. With an applied voltage, the optic axis **24** is tilted away from the cell normal,
FIG. 2B. In the OFF state, light does not see the birefringence in the normal

30   direction **26,** giving the dark state that is close to that of orthogonally crossed
polarizers. However, obliquely propagated light **28** picks up birefringent phase
retardation giving light leakage. This results in a poor contrast ratio at a higher

viewing angle as shown in FIG. 2C. FIG. 2C includes azimuth angles of 0, 45, 90, 135, 180, 225, 270 and 315 degrees, as represented along the circumference, and polar angles of 0, 20 and 60 degrees, as represented by the concentric circles. The outermost circle corresponds to the polar angle of 80 degrees. FIG. 2C shows an

5   extremely limited area inside of the high 100 iso-contrast line indicating insufficient viewing angle performance.

For increasing contrast, it is necessary to decrease the light leakage in the dark state as much as possible. If a sufficiently dark state cannot be obtained in an oblique direction, as mentioned above, the display quality will be

10   undesirably low.

Various methods to attain a higher contrast ratio at off axis incidence have been proposed. Clerc *et al.* suggested in U.S. Patent No. 4,701,028 using quarter wave plates in combination with linear polarizer. Thus, for the normal incidence in the OFF state, the propagating light is circularly

15   polarized. With the exit circular polarizer being orthogonal to the entrance one, the out coming light is extinguished. In off-axis case, the light becomes elliptically polarized with respect to the entrance polarizer. The cell thickness is adjusted so that the light after propagating through the cell obliquely is still absorbed at the exit polarizer regardless of the angle.

20   Takeda *et al.* disclosed the multi domain vertically aligned liquid crystal display in European Patent EP 0 884 626 A2. Liquid crystal pixels are divided so that the tilt direction of liquid crystal molecule 11 in the OFF state FIG. 1 varies from pixel to pixel. By making director field more symmetric, it gives a good viewing angle characteristic. However, the process of making multi-domain

25   adds extra cost and difficulty to display manufacturing.

The compensation film approach is another method that has been applied to improve the off-axis viewing characteristics. In its simplest scheme such as the one set forth in U.S. Patent 5,039,185, a film with negative optical anisotropy 30 normal to the film surface is used to compensate the-off axis

30   birefringence, FIG. 3A. The combination of two or more uniaxial or biaxial films gives a film with negative anisotropy its optical property represented by index ellipsoid 19. The viewing angle characteristic of this scheme is shown in FIG. 3B.

—

In comparison to FIG. 2C, the iso-contrast line 50 has been expanded to 60° and 40° in the horizontal and vertical direction, respectively. In relative diagonal directions (45°/225°, 135°/315° in azimuth angle), it extends up to 80° giving wider area with contrast of 50. Film's optical properties and thickness are

5 controlled by the requirement that the total phase retardation is zero in any direction of viewing. Based on a similar idea, V. Sergan *et al.* (V. Sergan, P.J. Bos and G. D. Sharp, SID 00 Digest, pp838-841 (2000)) used crossed plates with in-plane phase retardation in place of a negative film.

U.S. Patent 5,298,199 discloses a somewhat more sophisticated

10 application of biaxial film for compensation. In this patent, Hirose *et al.* suggests using biaxial film with the indices of refraction satisfying $n_z < n_y < n_x$, and x, y and z corresponding to the directions given by the coordinate system **10**. The addition of in-plane phase retardation $(n_x - n_y)d$, where d is a film thickness, decreases the on-axis transmission at non-zero applied voltage for OFF state. This enables one

15 to shorten the switching time between the ON and OFF states, while out of plane negative birefringence compensates the oblique angle phase retardation.

Aminaka *et al.* suggested a compensation scheme by films containing liquid crystal polymers with discotic mesogen in U.S. Patent 6,08,312. The discotic compound used is a negatively birefringent material. Inside of these

20 films, the direction of mesogen continuously changes. The idea is to mimic the director field near the surface so as to compensate the asymmetrical viewing angle while voltage is being applied to the cell.

From a different perspective, Ohmuro *et al.* gave a combination of negative plate **30** and positive plate **27** with axis set on the normal direction of the

25 polarizers (K. Ohmuro, S. Kataoka, T. Sasaki and Y. Koike, SID 97 Digest, pp. 845-848, U.S. Patent 6,141,075), FIG. 4A. J. Chen *et al.*, after careful examination of the above configuration, came to realize the importance of compensation of crossed polarizers (J. Chen *et al.*, SID 98 Digest, pp.315-318, (1998)). Crossed polarizers, when viewed from an off-normal direction, are no

30 longer orthogonal to each other and this fact leads to a leakage of light. Negative plates **30** (optical property represented by the ellipsoid **19**) with its optic axis in a thickness direction together with positive plates **27** with its axis parallel to the

polarizers' transmission axis gives superior performance. When it is applied to the vertically aligned cell, the contrast ratio at higher viewing angle is improved FIG. 4B compared to FIG. 3B. The contrast line 50 covers area further toward a higher polar angle. The 500 contrast line extends to $\pm45°$ and $\pm20°$ in horizontal and

5   vertical direction, respectively.

While the above-mentioned methods have improved the viewing quality of liquid crystal displays, the overall viewing angle remains poorer than it is desirable. It is a problem to be solved to provide a compensation film for a vertically-aligned liquid crystal cell that improves the viewing angle characteristic

10   of the display.

SUMMARY OF THE INVENTION

The invention provides an imaging component comprising a vertically aligned nematic liquid crystal cell, a polarizer, and a compensation film

15   containing a positive birefingent material oriented with the optic axis tilted in a plane perpendicular to the liquid crystal cell face. The invention also provides an electronic device containing the component of the invention as well as methods for preparing the component of the invention.

The invention enables an improved viewing angle characteristic.

20

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic showing the operation of the vertically aligned liquid crystal cell imaging component.

FIG. 2A, 2B are cross sectional views showing schematically the

25   OFF and ON state of FIG. 1. FIG. 2C is a viewing angle characteristic (VAC), diagram showing the viewing angle characteristic of a vertically aligned liquid crystal display without compensation film.

FIG. 3A is a schematic diagram of a prior art device with negative birefringent film. FIG. 3B shows the VAC of a vertically aligned liquid crystal

30   display with negative birefringent film.

83664US1/AEK

FIG. 4A is another schematic diagram of one of the prior art devices with negative and positive birefringent films. FIG. 4B shows the VAC of that device.

FIG. 5A, 5B and 5C are cross sectional diagrams of the configuration of one imaging component in accordance with the invention.

FIG. 6A shows a positive birefringent ellipsoid representing the constituent material for the anisotropic layer of the invention disposed on the base film. In FIG. 6B, the optic axis is shown tilted uniformly while it varies in the thickness direction in FIG. 6C. FIG. 6D is a diagram of the use of two positive birefringent layers arrangement on a base.

FIG.7A, 7B and 7C show three examples of orientation of the compensation film having one positive birefringent layer with respect to the transmission axis of the polarizer.

FIG. 8A, 8B and 8C show three examples of orientation of compensation layers having two positive birefringent layers with different thickness, relative to the polarizer.

FIG. 9A, 9B, and 9C show the results of simulation for VAC of the display with various compensation film arrangements of the invention.

FIG. 10A through 10D illustrates embodiments of display device components according to the invention. FIG.10E and FIG.10F illustrate embodiments of a reflective display.

DETAILED DESCRIPTION OF THE INVENTION

The current invention regarding the vertically aligned liquid crystal display with the optical compensation film described by referring to the drawings as follows.

FIG.2 is a mode of operation of a vertically aligned liquid crystal cell display in a cross sectional view. A vertically aligned liquid crystal is one in which the positive birefringent materials are oriented in a direction normal ($\pm$ 10°) to the surface of the cell. When the field is OFF, FIG. 2A, the optic axis of liquid crystal molecules 22 are almost perpendicular to the cell substrate 20. With the

applied field, the optic axis **24** tilts away from the normal as shown in FIG. 2B, and it gives the ON state. In the OFF state with normal viewing **26**, the incoming light does not see any birefringence. If this cell is placed between the crossed polarizers, it results in a dark state. However, in the oblique direction **28**,

5   propagating light suffers birefringence, giving leakage of light. This is the source of poor contrast at the higher viewing angle as shown in FIG. 2C. It is the scope of this invention to compensate dark state of the vertically aligned liquid crystal cell to yield high contrast in extended viewing angle. In some cases, the dark state may even correspond to the one with a small field applied, in which its optic axis

10   slightly changes from the state with a zero field. The compensation is achieved by combining a compensation film containing a positive birefingent material oriented with the optic axis tilted in a plane perpendicular to the liquid crystal cell face with a liquid crystal cell. Due to this feature, the current invention can compensate the dark state with or without applied fields.

15   In FIG. 5, three possible configurations of the display according to the invention are shown. FIG. 5A has one optical compensation film **36** inserted between polarizer **32** and liquid crystal cell **34** while FIG. 5B has an additional compensation film **40** between the liquid crystal cell **34** and polarizer **38**. FIG.5C is a scheme for reflective type display. It has one compensation film **36** placed

20   between the cell **34** and polarizer **38** and has light reflection plate **33**. Also for reflection type devices, additional plate with in-plane phase retardation **39** in the direction of the tilt direction of liquid crystal molecule **11** has to be inserted.

Now the actual inner structure of compensation film is described. The compensation film in accordance with this invention has more than one

25   optically positive birefringent layers disposed on base film. The positive birefringent layers contain the material with optical property of uniaxial or biaxial nature. The direction of optic axis of the material is fixed in one azimuth angle on the film plane. In case of material with the uniaxial nature, it has positive birefringence because it has two equivalent indices n_1 and n_2 that are smaller than

30   n_3 represented by index of ellipsoid **42** as shown in FIG. 6A. In this case, the direction of optic axis **43** corresponds to that of the maximum refraction index, n_3. In biaxial case, all of n's assume different values and the optic axis does not

giving more symmetric shape compared with FIG. 4B. Current inventors also found other placement of positive and negative birefringent plates such as given in FIG.7B and 7C have the compensating function.

The compensation layers of FIG. 6D contain two positive
5   birefringent layers **56** and **58** with a different thickness disposed on the base film **44**. The film plane projection of optic axis in two layers **60** and **62** are orthogonal to each other. In this case, the base **44** may or may not have a negative birefringence in the film normal direction. FIG.8A, 8B and 8C illustrate the three examples of placement of this type of compensation film **72** with respect to the
10   adjacent polarizer **68**. In 8A, the azimuth ϕ_2 of the thicker layer **58** is equal to the azimuth ϕ_1 of transmission axis **70** of polarizer **68**, and the azimuth ϕ_3 of the thinner layer **56** is equal to $90+\phi_2$. The thinner layer **56** is closer to the polarizers **68** than the thicker layer **58.** In 8B, azimuth ϕ_2 is perpendicular to that of thinner layer ϕ_3 and polarizer's transmission axis ϕ_1. Azimuths ϕ_1 and ϕ_3 are equal. The
15   thinner layer **56** side is facing to the polarizer **70**. In 8C, positive birefringent layer **58** is in contact with the adjacent polarizer **68**. Here the azimuth ϕ_1 is parallel to that of the thicker layer **58** ϕ_2. The azimuth ϕ_3 of the thinner layer **56** satisfies $\phi_3 = \phi_1 + 90°$.

FIG. 10A through 10F show the overall schematic diagram of one
20   embodiment according to the invention. Configuration 10A has one compensation film **74** on one side of the liquid crystal cell **14**. A pair of polarizers **12** and **18**, are disposed on opposite sides of the vertically aligned liquid crystal cell. Their transmission axes (polarization axes) **82** and **76** are orthogonally crossed with respect to each other in a direction normal to the cell surface, and
25   form a 45 degree angle with respect to the tilt direction of liquid crystal molecules **80**. For a film with one positive birefringent layer, a projection **66** of optic axis **42** in positive birefringent layer **64** of FIG.7A and 7C correspond to the direction specified by **78** in FIG.10A. FIG.10B is a diagram for the configuration given in FIG.7B. The direction **78** is now perpendicular to **76**. In case of a compensation
30   film with two positive birefringent layers disposed on the base film, it is a projection of the optic axis **62** of thicker layer **58** in FIG. 8A, 8B and 8C that

-9-

correspond to **78**. FIG. 10C and 10D are configuration with two compensation

films **74** and **84**. **84** has a direction **86** indicating the direction equivalent to **66** for

single and **62** for two positive birefringent layer compensation film. The principle

of placement is the same as the one compensation film case, FIG. 10 A and 10B.

5   FIG.10E and FIG.10F show the vertically aligned liquid crystal cell disposed

between the polarizer and a reflective plate, with the compensation film disposed

between the vertically aligned cell and the polarizer. **88** is a reflective plate, such

as mirror. One compensation film **84** is inserted between the liquid crystal cell **14**

and the polarizer **12**. Also, additional plate **90** with in-plane phase retardation is

10 placed. The direction **86** is paralell (FIG.10E) or perpendicular (FIG.10F) to **82**.

The compensation film in accordance with the present invention

can be produced by various methods. One example is a photo-alignment method

as it was suggested by Schadt *et al.* (Japanese Journal of Applied Physics, Part 2

(Letters) v 34 n 6 1995 pp.L764-767) . For example, a thin alignment layer is

15 coated on the base film followed by radiation of polarized light. Liquid crystal

monomer is then coated on the alignment layer and polymerized by further

radiation. The tilt of optic axis in positive birefringent film depends on the

radiation angle, thickness of anisotropic layers as well as properties of materials.

Also, desired alignment can be obtained by mechanically rubbed surface of

20 alignment layer. Other known methods employ shear orientation and the effect of

an electric or magnetic field.

In the following, preferable optical properties of optical

compensation film such as thickness and optic axis tilt are given. The positive

phase retardation from the liquid crystal cell in the OFF state ΔR, is

25 approximately,

$$\Delta R = (n_e - n_o)d_c, \qquad (1)$$

where n_e and n_o are the extraordinary and ordinary index of refraction for liquid

crystal. d_c is the thickness of the cell. A film with $-\Delta R$ is needed for

compensating the vertically aligned liquid crystal with small tilt angle and without

30 an external field applied. Optimization of crossed polarizers requires combination

of in-plane and out of plane phase retardation. In the following, the retardation of

83664US1/AEK

-10-

the positive birefringent layer according to the present invention is given

by $\Delta R_a = (n_3 - n_1)d$, where $(n_3 - n_1)$ is the birefringence and d is thickness. Since the

positive birefringent material has its optic axis tilted in a plane perpendicular to

the liquid crystal cell face, this material contributes both in-plane and out of plane

5   retardation ΔR_c. The total out of plane retardation ΔR_T provided by the base film

depends on ΔR_c and ΔR . In configuration given in FIG.7A, ΔR_a is preferably

between $20nm < \Delta R_a < 50nm$ or more preferably, $30nm < \Delta R_a < 40nm$, if two

films are placed on both sides of the liquid crystal cell as FIG.10C. For ΔR_T,

$0.6\Delta R_c < \Delta R_T < 0.9\Delta R_c$ or more preferably, $0.7\Delta R_c < \Delta R_T < 0.8\Delta R_c$.

10   For compensation films **48** and **52** in this invention, the negative

retardation ΔR_T is from the base film **44** while anisotropic layer **46** and **50**

contribute ΔR_a. In the example 7A, the tilt θ_1 as specified in FIG.6B, satisfies

the relation $10^\circ \le \theta_1 \le 40^\circ$ or preferably, $20^\circ \le \theta_1 \le 30^\circ$. For varying tilt as in

FIG.6C, θ_2 and θ_3 are in the range: $30^\circ \le \theta_2 \le 60^\circ$, $0^\circ \le \theta_3 \le 30^\circ$ or more

15   preferably $40^\circ \le \theta_2 \le 50^\circ$ and $0^\circ \le \theta_3 \le 10^\circ$ for the best performance. We can

have a reversed tilt change as well. In this case, θ_2 and θ_3 satisfy, $0^\circ \le \theta_2 \le 30^\circ$

and $30^\circ \le \theta_3 \le 60^\circ$ or more preferably $0^\circ \le \theta_2 \le 10^\circ$ and $40^\circ \le \theta_3 \le 50^\circ$. In 7B

and 7C, θ_1 satisfies $3^\circ \le \theta_1 \le 10^\circ$ or for the best performance $5^\circ \le \theta_1 \le 7^\circ$. For

varying tilt as in FIG.6C, θ_2 and θ_3 are in the range specified by $0^\circ \le \theta_2 \le 8^\circ$,

20     $6^\circ \le \theta_3 \le 12^\circ$ or more preferably, $0^\circ \le \theta_2 \le 3^\circ$, $7^\circ \le \theta_3 \le 10^\circ$. As for the case of

7A, reverse tilt (exchanging θ_2 and θ_3 in the above relation) is also acceptable.

             Compensation film **54** is different from **48** and **52**. In this case, the

crossed positive birefringent layers on the base film contribute both of out of

plane ΔR_T and in-plane retardation. Therefore, base film **44** may be optically

25   isotropic. The equal thickness portion of two layers has phase retardation ΔR_T,

and the residual thickness $|d_1 - d_2|$ contributes in-plane retardation.

             The optically anisotropic compensation film is comprised of at

least one positive birefringent layer disposed on a base film. If more than two

83664US1/AEK

-11-

layers are disposed, they may or may not have an equal thickness. Inside a single positive birefringent layer, the direction of optic axis stays constantly tilted or varies across the thickness. In some cases, the direction changes continuously throughout the thickness in a plane perpendicular to the layer. If there are more

5   than two positive birefringent layers disposed on the base film, the projection of optic axis on the film plane of each layer are orthogonal. The base film may or may not be birefringent.

The invention may be used in conjunction with electronic liquid crystal display devices. The energy required to achieve this control is generally

10   much less than that required for the luminescent materials used in other display types such as cathode ray tubes. Accordingly, LC technology is used for a number of applications, including but not limited to digital watches, calculators, portable computers, electronic games for which light weight, low power consumption and long operating life are important features.

15   Active-matrix liquid crystal displays (LCDs) use thin film transistors (TFTs) as a switching device for driving each liquid crystal pixel. These LCDs can display higher-definition images without cross talk because the individual liquid crystal pixels can be selectively driven.

Ordinary light from an incandescent bulb or from the sun is randomly

20   polarized, that is, it includes waves that are oriented in all possible directions. A polarizer is a dichroic material that functions to convert a randomly polarized ("unpolarized") beam of light into a polarized one by selective removal of one of the two perpendicular plane-polarized components from the incident light beam. Linear polarizers are a key component of liquid-crystal display (LCD) devices.

25   There are several types of high dichroic ratio polarizers possessing sufficient optical performance for use in LCD devices. These polarizers are made of thin sheets of materials, which transmit one polarization component and absorb the other mutually orthogonal component (this effect is known as dichroism). The most commonly used plastic sheet polarizers are composed of a thin, uniaxially-

30   stretched polyvinyl alcohol (PVA) film, which aligns the PVA polymer chains in a more-or-less parallel fashion. The aligned PVA is then doped with iodine molecules or a combination of colored dichroic dyes (see, for example, EP 0 182

83664US1/AEK

632 A2, Sumitomo Chemical Company, Limited), which adsorb to and become uniaxially oriented by the PVA to produce a highly anisotropic matrix with a neutral gray coloration. To mechanically support the fragile PVA film it is then laminated on both sides with stiff layers of triacetyl cellulose (TAC), or similar

5   support.

Contrast, color reproduction, and stable gray scale intensities are important quality attributes for electronic displays, which employ liquid crystal technology. The primary factor limiting the contrast of a liquid crystal display is the propensity for light to "leak" through liquid crystal elements or cell, which are in

10   the dark or "black" pixel state. Furthermore, the leakage and hence contrast of a liquid crystal display are also dependent on the angle from which the display screen is viewed. Typically the optimum contrast is observed only within a narrow viewing angle centered about the normal incidence to the display and falls off rapidly as the viewing angle is increased. In color displays, the leakage

15   problem not only degrades the contrast but also causes color or hue shifts with an associated degradation of color reproduction. In addition to black-state light leakage, the narrow viewing angle problem in typical twisted nematic liquid crystal displays is exacerbated by a shift in the brightness-voltage curve as a function of viewing angle because of the optical anisotropy of the liquid crystal

20   material.

In the following examples, liquid crystal MLC6048 from Merck Inc. is used. The cell thickness is 4.2micron, which makes $\Delta R = 328nm$. Pre-tilt at the boundaries in OFF state is 3° measured from the cell normal direction.

25   Example 1

The compensation film 48 in FIG.6B has $\theta_1 = 20°$. The retardation ΔR_a from the positive birefringent material and retardation ΔR_r from the base are 47nm and − 130nm, respectively. The film is positioned as shown in FIG.7A with respect to the polarizer. Two compensation films are used following the configuration given

30   in FIG.10C. The VAC is given in FIG.9A in terms of an iso-contrast plot.

Example 2

The compensation film **48** in FIG.6C with $\theta_2 = 40^o$ and $\theta_3 = 0^o$. ΔR_a and ΔR_T are 47nm and −130nm, respectively. The film is positioned as shown in FIG.7A with respect to the polarizer. Two compensation films are used following

5   the configuration given in FIG.10C. The VAC is given in FIG.9B in terms of an isocontrast plot.

Example 3

The compensation film **54** according to FIG.6D, where with $\theta_1 = 5^o$. The film is

10   positioned according to FIG.8C. The base layer is optically isotropic and does not have phase retardation. The layer d_1 has phase retardation of 180nm and d_2 has 70nm. Two compensation films are used following the configuration in FIG.10C. The VAC is given in FIG.9D.

15   The entire contents of the patents and other publications referred to in this specification are incorporated herein by reference.

20

Parts List

    10 xyz coordinate system

    11 tilt direction of liquid crystal molecules

    12 polarizer

    14 vertically aligned liquid crystal cell

    16 voltage source

    18 polarizer

    19 ellipsoid of index representing optical properties of plate **30**

    20 cell substrate

    22 optic axis in almost vertical direction

    24 optic axis tilted

    26 light propagating in the vertical direction

    27 compensation film with in-plane phase retardation

    28 light propagating in the oblique direction

    29 ellipsoid of index representing optical properties of plate **27**

    30 compensation film with out of plane negative phase retardation

    31 cross sectional view of the device with one compensation film according to the invention.

    32 polarizer

    33 light reflecting plate

    34 liquid crystal cell

    35 cross sectional view of the device with two compensation films according to the invention

    36 compensation film

    37 cross sectional view of the reflection type device according to the invention

    38 polarizer

    40 compensation film

    42 index of ellipsoid representing optical properties of constituent material of positive birefringent layer

    43 optic axis

44 base film of compensation film

45 liquid crystal cell

46 optically positive birefringent layer with uniform tilt in optic axis

48 compensation film with uniform tilt layer **46**

50 optically positive birefringent layer with varying tilt in optic axis

52 compensation film with varying tilt layer **50**

54 compensation film with two positive birefringent layers **56** and **58** on the base film **44**

56 positive birefringent layer in contact with the base film **44**

58 top positive birefringent layer

60 projection of optic axis of the layer **58**

62 projection of optic axis of the layer **56**

64 anisotropic layer with positive birefringence

66 projection of optic axis **42**

68 polarizer

70 direction of transmission axis of the polarizer **68**

72 compensation film with two positive birefringent layers **56** and **58** on the base film **44**

74 compensation film

76 transmission axis of polarizer **18**

78 direction of in-plane phase retardation of the compensation film **74**

80 tilt direction of liquid crystal molecule

82 transmission axis of polarizer **12**

84 compensation film

86 direction of in-plane phase retardation of the compensation film **84**

88 reflection plate

90 plate with in-plane retardation in the direction of **80**